

[hanp HPP2015 Evaluation Test Report]



Item : HPP2015

Test date : 2015. 12. 01

Standard (Drum/Toner) : Original/Original

Test pattern : Adobe Reader LSA Mono 5%

Test (Drum/Toner) : hanp HP1320-2 / HP1320 Universal

Test page : 1 ~ 3,000age

Purpose of the test : Toner Matching Test



Model of printer : HPP2015

◆ Test Condition

Temp.	Relative Humidity	P.C.R	Developer / R	D / Blade	W / Blade
24±3℃	50±10%			OEM 1 Cycle	



◆ Density & Adhesion

page	Original/Original				hanp HP1320-2 / THP1320 Universal			
	Black	Gray	White	Adhesion	Black	Gray	White	Adhesion
Start	1.41	0.42	0.06	98.0%	1.44	0.44	0.05	97.0%
END	1.42	0.43	0.05	99.0%	1.45	0.46	0.05	98.0%



◆ Toner Yield & Durability

	Toner Consumption (Average)	G.P.P (Average)	P.P.G (Average)	Transfer rate (Average)	Expected toner yield	Coating thickness		
						Top	Middle	Bottom
						(g)	(g/page)	(page/g)
Original/Original	36.5	0.0365	27.40	89.91		1.1	1.2	1.2
hanp HP1320-2 / THP1320 Universal	42.7	0.0427	23.44	91.38		1.0	1.0	1.1



◆ Notice

	Ghost	Back Ground	Filming	Peel Off	Adhesion	Line test
Original/Original	◎	○	◎	◎	◎	○
hanp HP1320-2 / THP1320 Universal	○	◎	◎	◎	◎	○

*Evaluation
 ◎ Very good X Poor
 ○ Good XX Bad
 △ Acceptable

◆ Test Result
